

Crosslinker 100 / 200 series

Crosslinker for vinyl-functional silicone polymers

The cross-linkers of the Cross-linker 100 and 200 series are polydimethyl siloxanes comprising SiH groups in the polymer chain. The cross-linkers of the Crosslinker 200 series additionally have terminal SiH groups. Both cross-linker types are used in polyaddition silicones.

Both series are available with different viscosity levels and SiH contents. Other SiH contents and viscosity levels can be delivered upon request.

Technical data (no specification)

Product name	SiH content [mmol/g]	Viscosity at 25 °C [mPas]	Refractive index n_D^{20}
Crosslinker 100	7.8	45	1.4020
Crosslinker 101	4.3	45	1.4025
Crosslinker 110	3.8	100	1.4030
Crosslinker 120	1.1	500	1.4045
Crosslinker 180	1.9	50	1.4035
Crosslinker 190	16	20	1.3975
Crosslinker 200	3.2	50	1.4030
Crosslinker 210	4.2	40	1.4025

Technical data (no specification)

Property	Unit	
Appearance		clear, colourless liquid
Density (20 °C)	[g/cm ³]	approx. 1

Application

When working with two-component silicone formulations, it must be ensured that Pt-catalyst (e. g. Catalyst 500 series) and SiH cross-linkers are kept strictly separated. Single-component addition silicones, for which specially protected catalysts (e. g. Catalyst XP 2471) are used, represent an exception.

In general, the composition must be selected so that the total formulation contains approximately a double molar excess of SiH groups as compared with vinyl groups.

Further information about the formulation structure is available upon request.

Packaging and Storage

Packaging	190 kg drum, 950 kg IBC PE
Shelf life	24 months in originally sealed containers
Storage	Dry, up to 30 °C (86 °F) in sealed containers, do not permanently expose to intensive sunlight.

Safety and Handling

The rules and regulations for the handling and use of chemicals have to be observed. Please refer to the Material Safety Data Sheets for further details.

Attention must in particular be paid to the fact that silicones containing SiH may generate hazardous hydrogen gas in connection with certain pollutants. For further information, please consult e. g. www.silicones-safety.com.

11/2016

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

(Status: August 2014)

Evonik Nutrition & Care GmbH

Charlottenburger Str. 9, 21502 Geesthacht, Germany

Phone: +49 4152 8092-0, Fax: 49 4152 79156

nano-and-silicone-technology@evonik.com, www.evonik.com/nano-and-silicone-technology