

NANOPOX® A 410

NANOPOX® A 410 is a high performance, versatile, silica reinforced Bisphenol A based epoxy resin for the use in adhesives. The silica phase consists of surface-modified synthetic SiO₂ nanospheres of very small size (average diameter of 20 nm) with a narrow particle size distribution (maximum diameter 50 nm). Despite the high SiO₂ content of 40 wt%, NANOPOX® A 410 has a comparatively low viscosity due to the agglomerate-free colloidal dispersion of the nanoparticles in the resin.

Technical data (no specification)

Property	Units	Typical Values
Base resin		Bisphenol A diglycidyl ether
Appearance		opaque liquid
SiO ₂ -content	[wt%]	40
Density @ 20 °C	[g/ml]	1,4
Viscosity @ 25 °C	[mPas]	60 000
Epoxy equivalent weight	[g/eq]	295
Shelf life	[months]	6*

*if stored in the original unopened container

Processing Instructions

NANOPOX® A 410 can be used as any other Bisphenol A diglycidyl ether. However, the colloidal silica in NANOPOX® products tends to agglomerate if the stabilisation is affected by inappropriate formulation components like hydrocarbon solvents (e. g. xylene). Therefore the compatibility between NANOPOX® A 410 and all other formulation components should be tested separately before starting formulation development.

Handling and Storage

NANOPOX® A 410 should be handled in accordance with good industrial practice. Detailed information is provided in the Material Safety Data Sheet.

Keep container(s) tightly closed when not in use!

NANOPOX® A 410 tends to crystallize at ambient temperatures. The product can be easily re-melted by heating it up to 70 °C for a short period of time.

11/2016

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

(Status: August 2014)

Evonik Nutrition & Care GmbH

Charlottenburger Str. 9, 21502 Geesthacht, Germany

Phone: +49 4152 8092-0, Fax: 49 4152 79156

nano-and-silicone-technology@evonik.com, www.evonik.com/nano-and-silicone-technology